

Product data**Suprasec 2067**

isocyanate

**Typical properties**

Product	Suprasec 2067
Appearance	Brown liquid
Density, g/cm ³ at 25°C	1.14
Viscosity, mPa s at 25°C	610
Isocyanate (NCO) value, % corrected for hydrolysable chlorine	19.30
Hydrolysable chlorine, ppm	< 2000
Flash Point, °C Cleveland Cup, ASTM method D92	> 100

Introduction

Suprasec® 2067 is a prepolymerised diphenyl methane diisocyanate (MDI).

Application

For information on this product, please contact us at ACE@huntsman.com; Other contact information is given on the second page.

Suprasec 2067

isocyanate

Storage and Handling Recommendations

Containers of Suprasec 2067 should be kept properly closed and stored indoors in a well-ventilated area under normal factory conditions. Storage at temperatures ranging from 20 - 30 °C provides a convenient viscosity for handling. Storage at low temperature is not recommended because it may lead to some crystallisation; this material must therefore be protected from frost. If under abnormal storage conditions some crystallisation does occur, the material should be melted according to the procedures given in the publication PU 181-15E. Storage at temperatures above 50°C is not recommended, since this can lead to the formation of insoluble solids and also the viscosity build-up increases on extended storage.

Under the recommended storage conditions and if protected from humidity and contaminants, i.e. in properly sealed drums, cans, etc., Suprasec 2067 has a provisional storage life of 9 months at the customer. In case of storage in bulk containers, please contact our Sales Representative for further details. Detailed information on how to obtain optimum bulk storage conditions, is available in the ISOPA document Guidelines for Safe Loading/Unloading, Transportation & Storage of TDI and MDI.

Reaction with atmospheric moisture, is prevented by storing Suprasec 2067 in carefully sealed containers under a dry air atmosphere. During handling, the product must be protected from water ingress and from atmospheric moisture. Containers should be re-sealed immediately after each sampling. The reaction of isocyanates with water leads to the formation of insoluble ureas and carbon dioxide gas, which can lead to pressure build-up in closed containers. Containers used for Suprasec 2067 must therefore be absolutely dry.

The precautions necessary when handling Suprasec 2067, i.e., MDI, and the decontamination procedures recommended to be used in case of spillage, are described fully in the publication PU 193-1E; MDI-based compositions: Hazards and safe-handling procedures. Should it prove necessary to melt Suprasec 2067, procedures are given in the publication PU 181-15E; Recommended melting procedures for MDI-based isocyanates.

Enquiries should be addressed to the nearest Huntsman Sales Office or to:
Huntsman ICI (Asia Pacific) Pte Ltd, 150 Beach Road, #14-05/08 Gateway West, Singapore 189720
Telephone (65) 6297 3363 Telefax (65) 6298 8606

The address of your nearest Technical Centre is:
Huntsman ICI (Asia Pacific) Pte Ltd, 150 Beach Road, #14-05/08 Gateway West, Singapore 189720
Telephone (65) 6297 3363 Telefax (65) 6298 8606

Huntsman Polyurethanes warrants only that its products meet the specifications agreed with the buyer. Typical properties, where stated, are to be considered as representative of current production and should not be treated as specifications. The manufacture of polyurethane materials and polymeric foams is the subject of granted patents and patent applications; freedom to operate patented processes is not implied by this publication. While all the information and recommendations in this publication are to the best of our knowledge, information and belief accurate at the date of publication, NOTHING HEREIN IS TO BE CONSTRUED AS A WARRANTY, EXPRESS OR OTHERWISE. IN ALL CASES, IT IS THE RESPONSIBILITY OF THE USER TO DETERMINE THE APPLICABILITY OF SUCH INFORMATION AND RECOMMENDATIONS AND THE SUITABILITY OF ANY PRODUCT FOR ITS OWN PARTICULAR PURPOSE. The behaviour of the products referred to in this publication in manufacturing processes and their suitability in any given end-use environment is dependent upon various conditions such as chemical compatibility, temperature, which are not known by Huntsman Polyurethanes. It is the responsibility of the user to evaluate the manufacturing circumstances and the final product under actual end-use requirements and to adequately advise and warn purchasers and users thereof. Products may be toxic and require special precautions in handling. The user should obtain from Huntsman Polyurethanes Safety Data Sheets containing detailed information on toxicity together with proper shipping, handling and storage procedures and should comply with all applicable safety and environmental standards. Hazards, toxicity and behaviour of the products may differ when used with other materials and is dependent on manufacturing circumstances or other processes. Such hazard, toxicity and behaviour should be determined by the user and made known to handlers, processors and end users. Except where explicitly agreed otherwise, the sale of products referred to in this publication is subject to the general terms and conditions of sale of Huntsman International LLC or of its affiliated companies. Huntsman Polyurethanes is an international business unit of Huntsman International LLC. Huntsman Polyurethanes trades through Huntsman affiliated companies in different countries such as Huntsman International LLC in the USA and Huntsman Holland BV in Western Europe.

'Suprasec' is a registered trademark of Huntsman International LLC. Copyright © 2001 Huntsman International LLC. All rights reserved.

Health and Safety Advice

The appropriate health and safety advice can be found in the safety data sheet for Suprasec 2067 available on request. The applicable Safety Data Sheet should be reviewed by customer before handling the Huntsman product.

All users of Suprasec 2067 are advised to read the publication PU 193-1E; MDI-based compositions: Hazards and safe-handling procedures.